




## 354 **Premium Grade Duct Tape**



| Backing:        | PE Coated Cloth           |                                  |  |  |
|-----------------|---------------------------|----------------------------------|--|--|
| Adhesive:       | Rubber                    |                                  |  |  |
| Liner:          | N/A                       |                                  |  |  |
| Colors:         | Silver, Black, Olive Drab |                                  |  |  |
| Specifications: |                           | Tested in accordance with UL 723 |  |  |
| Standard Sizes: |                           | 48mm x 55m, 72mm x 55m           |  |  |

| Applications                         |   |  |  |  |  |
|--------------------------------------|---|--|--|--|--|
| Heavy-duty repair & maintenance      | Waterproof packaging  |  |  |  |  |
| • Duct and vent sealing applications | Media-blast protection  |  |  |  |  |
| Features                             | Benefits  |  |  |  |  |
| PE-Coated Cloth Backing              | Smooth, consistent unwind                                     |  |  |  |  |
|                                      | <ul> <li>Moisture chemical and abrasion resistance</li> </ul> |  |  |  |  |

| • [ | Natural | rubber | based | adhesive |
|-----|---------|--------|-------|----------|
|-----|---------|--------|-------|----------|

Low VOC Content 

| • | Smooth, consistent unwind                      |
|---|--|
| • | Moisture, chemical and abrasion resistance     |
| • | High adhesion and excellent holding power      |
|   | Long-term water resistant bonds                |
| • | Can contribute toward satisfying EQ Credit 4.1 |
|   | (Low Emitting Materials) under LEED®           |
|   |  |

| Physical Properties   |              |            |             |  |  |  |
|-----------------------|--------------|------------|-------------|--|--|--|
|                       | Standard UOM | Metric UOM | Test Method |  |  |  |
| Total Thickness       | 13 mils      | 330.2 mic  | ASTM D-1000 |  |  |  |
| Adhesion to Steel     | 50 oz/in     | 5.47 N/cm  | PSTC-101    |  |  |  |
| Tensile Strength      | 29 lb/in     | 50.79 N/cm | ASTM D-1000 |  |  |  |
| Operating Temperature | 40-200°F     | 4-93°C     |             |  |  |  |
| VOC Content           | <1 g/L       |            |             |  |  |  |

Recommended Storage Conditions: 40-60% Humidity, 60°F-80°F Standard Shelf Life (at 25C): 36 months from date of manufacture.

The information presented herein was prepared at BERRY PLASTICS CORPORATION (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To Berry Plastics' knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are typical values submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY PLASTICS assumes any legal responsibility.